

DuPont Packaging & Industrial Polymers

Elvax® resins



DuPont™ Elvax® 265

Description

Generic Name	Ethylene Vinyl Acetate
Product Description	DuPont™ Elvax® 265 is an ethylene-vinyl acetate copolymer resin for use in industrial applications.

Product Characteristics

Processing Method	* Extrusion
Typical Applications	Elvax® 265 resins can be used for the following applications: molding, compounding and extrusion; wire and cable; and adhesives, sealants, and wax blends. For additional information and properties associated with specific application, please refer to the Grade Selector Guides found on the Elvax® website for industrial applications, http://www.dupont.com/industrial-polymers/elvax/index.html .
Material Status	* Commercial: Active
Availability	* Globally
Composition	* 28 %, By Weight, Vinyl Acetate * BHT antioxidant
Uses	* Industrial Applications
Manufacturer / Supplier	* DuPont Packaging & Industrial Polymers

Properties

Physical

Density	0.955g/cm³	ASTM D1505
Density	0.951g/cm³	ASTM D792 – ISO 1183
Melt Index (190°C/2.16kg)	3g/10 min	ASTM D1238 – ISO 1133

Thermal

Thermal	Nominal Values	Test Method
Melting Point	73°C (163°F)	ASTM D3418 – ISO 3146
Vicat Softening Point	49°C (120°F)	ASTM D1525 – ISO 306
Cloud Point in Paraffin Wax	66°C (151°F)	Note: 10% Elvax® in fully refined paraffin wax, 146 AMP. Incompatible at temperatures up to 177°C (350°F).
Softening Point Ring and Ball	171°C (340°F)	ASTM E28
Brittleness Temperature	–100°C (–148°F)	ASTM D746

high density

Hardness	Nominal Values	Test Method
Durometer Hardness (Shore A)	86	ASTM D2240 – ISO 868

Processing Information

General Processing Information

Elvax® resins can be processed by conventional thermoplastic processing techniques, including injection molding, structural foam molding, sheet and shape extrusion, blow molding and wire coating. They can also be processed using conventional rubber processing techniques such as Banbury, two-roll milling and compression molding.

Elvax can be used in conventional extrusion equipment designed to process polyethylene resins. However, corrosion-protected barrels, screws, adapters, and dies are recommended, since, at sustained melt temperatures above 446°F (230°C), ethylene vinyl acetate (EVA) resins may thermally degrade and release corrosive by-products.

FDA Status

Elvax® 265 EVA Resin complies with Food and Drug Administration Regulation 21 CFR 177.1350(a)(1) – – Ethylene-vinyl acetate copolymers, subject to the limitations and requirements therein. This Regulation describes polymers that may be used in contact with food, subject to the finished food-contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (b)(1) of the Regulation.

Safety & Handling

A Product Safety Bulletin, Material Safety Data Sheet, and more detailed information on compounding and processing Elvax® resins for specific applications are available from your DuPont Packaging and Industrial Polymers representative.

Read and understand the Material Safety Data Sheet (MSDS) before using this product

DuPont Worldwide

Asia Pacific

DuPont Singapore PTE Ltd.
1 Maritime Square #07-01
World Trade Centre
Singapore 0409
Telephone 65-273-2244
Fax 65-272-7494

Australia

DuPont (Australia) Ltd.
254 Canterbury Road
Bayswater, Victoria 3153
Australia
Telephone 3-9721-5900
Fax 3-9721-5650

Brazil/South America

DuPont do Brasil, S.A.
Alameda Itapecuru, 506
06454-080 Barueri, SP Brasil
Telephone 5-11-74166-8542 /
8393
Fax 55-11-4166-8720

Canada

DuPont Canada Inc.
P.O. Box 2200, Streetsville
7070 Mississauga, Road
Mississauga, ONT L5M 2H3
Telephone (Canada Only):
800-268-3943 /
905-821 5953
Fax 905-821-5230

Europe

DuPont de Nemours Int'l.
S.A.
2, Chemin du Pavillon Box 50
CH-1218 Le Grand Saconnex
Geneva, Switzerland
Telephone 022-717-51-11
Fax 022-717-55-00

Japan

Mitsui-DuPont
Polychemicals Co., Ltd.
Kasumigaseki Bldg. 24F
3-2-5 Kasumigaseki
Chiyoda-ku, Tokyo 100, Japan
Telephone 813-3580-5531
Fax 813-3592-1540

Mexico/Central America

DuPont, S.A. de C.V.
Homero 206 Anexo Planta Alta
Col. Chapultepec Morales
11570, D.F. Mexico
Telephone 52-55-57-22-1000
Fax 52-55-57-22-1308

United States

DuPont Packaging and
Industrial Polymers
Barley Mill Plaza 26-2122
Lancaster Pike & Route 141
P.O. Box 80026
Wilmington, DE 19880-0026
Telephone 302-774-1161
Toll-free (USA) 800-438-7225
Fax 302-999-4399

<http://www.dupont.com/>
info@dupont.com

Because DuPont cannot anticipate or control the many different conditions under which this information and/or product may be used, it does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. Users of DuPont products should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties but they should not be used to establish specification limits or used alone as the basis of design.

Disclosure of this information is not a license to operate or a recommendation to infringe a patent of DuPont or others.

Copyright© 1995-2004. E.I. duPont de Nemours and Company. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ™ or ® are trademarks or registered trademarks of E.I. duPont de Nemours and Company or its affiliates.

This data sheet is effective as of 4/5/2005, and supersedes all previous versions.



The miracles of science®

ExxonMobil LLDPE

LL 1004YB

Wire & Cable Resin

Description

LL 1004YB is a C₄ Ziegler Natta LLDPE, especially designed for Low Voltage power cable insulation, using the two-step silane cross-linking process.

The grade contains a higher level of antioxidants and has excellent Environmental Stress Crack Resistance (ESCR).

Sufficient Cu-inhibitor should be added to meet specific ageing requirements for insulation.

For jacketing applications, addition of Carbon Black or UV stabilizer is required.

Applications

- Two-step Silane cross-linkable insulation for Low Voltage power installation cable
- Two-step silane cross-linkable insulation for Arial Bundle Cable
- Telecom or Low Voltage power cable jacketing

Additive Package	Antiblock	Slip	Thermal Stabilizer
LL 1004YB	No	No	Yes

Resin Properties	Test Based On	Typical Value / Unit	
Melt Index	ASTM D 1238	2.8 g/10 min	
Density	ExxonMobil Method	0.918 g/cm ³	
Peak Melting Temperature	ExxonMobil Method	121 °C	250 °F

low density

Molded Properties¹

Flexural Modulus, 1% Secant	ASTM D 790	251 MPa	36000 psi
Tensile Strength at Yield	ASTM D 638	12 MPa	1740 psi
Tensile Strength at Break	ASTM D 638	13 MPa	1890 psi
Elongation at Yield	ASTM D 638	16 %	
Elongation at Break	ASTM D 638	710 %	
Shore Hardness – D (15s)	ASTM D 2240	48	
Volume Resistivity	ASTM D 257	6 * 10 ¹⁵ Ohm.cm	
Dielectric Constant (60 Hz)	ASTM D 150	2.17	
Dissipation Factor (60 Hz)	ASTM D 150	5.0 * 10 ⁻⁴	
Dielectric Strength (500V/sec)	ASTM D 149	53 V/μ	1340 V/mil

1. Specimens were compression molded in accordance with ASTM D 4703.

Revised January 2006

©2006 Exxon Mobil Corporation. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Emblem, and the "Interlocking X" Device are trademarks of Exxon Mobil Corporation.

ExxonMobil LLDPE

LL 1004YB

Wire & Cable Resin

Description

LL 1004YB is a C₄ Ziegler Natta LLDPE, especially designed for Low Voltage power cable insulation, using the two-step silane cross-linking process.

The grade contains a higher level of antioxidants and has excellent Environmental Stress Crack Resistance (ESCR).

Sufficient Cu-inhibitor should be added to meet specific ageing requirements for insulation.

For jacketing applications, addition of Carbon Black or UV stabilizer is required.

Applications

- Two-step Silane cross-linkable insulation for Low Voltage power installation cable
- Two-step silane cross-linkable insulation for Arial Bundle Cable
- Telecom or Low Voltage power cable jacketing

Additive Package	Antiblock	Slip	Thermal Stabilizer
LL 1004YB	No	No	Yes

Resin Properties	Test Based On	Typical Value / Unit	
Melt Index	ASTM D 1238	2.8 g/10 min	
Density	ExxonMobil Method	0.918 g/cm ³	
Peak Melting Temperature	ExxonMobil Method	121 °C	250 °F

Molded Properties¹

Flexural Modulus, 1% Secant	ASTM D 790	251 MPa	36000 psi
Tensile Strength at Yield	ASTM D 638	12 MPa	1740 psi
Tensile Strength at Break	ASTM D 638	13 MPa	1890 psi
Elongation at Yield	ASTM D 638	16 %	
Elongation at Break	ASTM D 638	710 %	
Shore Hardness – D (15s)	ASTM D 2240	48	
Volume Resistivity	ASTM D 257	6 * 10 ¹⁵ Ohm.cm	
Dielectric Constant (60 Hz)	ASTM D 150	2.17	
Dissipation Factor (60 Hz)	ASTM D 150	5.0 * 10 ⁻⁴	
Dielectric Strength (500V/sec)	ASTM D 149	53 V/μ	1340 V/mil

1. Specimens were compression molded in accordance with ASTM D 4703.

Revised January 2006

©2006 Exxon Mobil Corporation. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Emblem, and the "Interlocking X" Device are trademarks of Exxon Mobil Corporation.